



Expanko Resilient Flooring
 180 Gordon Drive | Suite 107 | Exton, PA 19341
 800.345.6202 | sales@expanko.com | www.expanko.com



CHEMICAL RESITANCE CHART

TECHNICAL SUPPORT 800.345.6202

ASTM F 925

Test Product	Sereniti Rubber Flooring Test Code
White Vinegar (5%)	0
Rubbing Alcohol (70%)	0
White Mineral Spirits	0
Sodium Hydroxide NaOH (5%)	1
Hydrochloric Acid HCl (5%)	0
Sulphuric Acid H ₂ SO ₄ (5%)	0
Ammonium Hydroxide NH ₄ OH (5%)	0
Bleach NaOCl (5.25%)	0
Disinfectant Phenol (5%)	0
Olive Oil	1
Gasoline	1
Kerosene	1
Providone-Iodine	1
Iodine	3
Wright's Blood Stain	3
Dustbane Germicide	1
Black Asphalt Emulsion	2
Peroxyde H ₂ O ₂	1
Cranberry Juice	1
Grape Juice	0
Beet Juice	1
Urine	0
Ketchup	0
Mustard	0
Betadine	1

- Tests conducted on products direct from production, without surface treatment
- One Hour Test Results
- Coding System of Results:
 - 0 = No Change
 - 1 = Slight Discoloration
 - 2 = Moderate Discoloration
 - 3 = Severe Discoloration

For more information on chemical resistance contact Expanko Resilient Flooring 800.345.6202