



Expanko Resilient Flooring  
180 Gordon Drive | Suite 107 | Exton, PA 19341  
800.345.6202 | sales@expanko.com | www.expanko.com

# REZTEC

RECYCLED RUBBER FLOORING

## MATERIALS SAFETY DATA SHEET

**TECHNICAL SUPPORT 800.345.6202**

CHEMICAL NAME: DIPHENYLMETHANE DIISOCYANATE  
(MDI) MODIFIED  
TRADE NAME: REZTEC RUBBER FLOORING

### HAZARDOUS INGREDIENTS

PHYSICAL DATA: N/A  
BOILING POINT: N/A  
SPECIFIC GRAVITY (H<sub>2</sub>O=1): 0.9  
VAPOR PRESSURE (MM HG.): N/A  
PERCENT, VOLATILE BY VOLUME: (%)  
VAPOR DENSITY (AIR=1): N/A  
EVAPORATION RATE (\_\_\_\_=1): N/A  
SOLUBILITY IN WATER: N/A  
APPEARANCE AND ODOR: BLACK/ WITH SLIGHT ODOR

### SPECIAL PROTECTION INFORMATION

RESPIRATORY PROTECTION: N/A  
VENTILATION - LOCAL EXHAUST: N/A  
MECHANICAL: N/A  
PROTECTIVE GLOVES: N/A  
EYE PROTECTION: N/A  
OTHER PROTECTIVE EQUIPMENT: N/A

### SPECIAL PRECAUTIONS

TO BE TAKEN IN HANDLING AND STORAGE: AVOID CONTACT WITH FLAME AND EXCESSIVE RADIANT HEAT

### FIRE AND EXPLOSION HAZARD DATA

FLASH POINT (METHOD USED): N/A  
FLAMMABLE LIMITS: N/A  
EXTINGUISHING MEDIA: CO<sub>2</sub>, DRY CHEMICAL, COPIOUS  
SPECIAL FIRE FIGHTING PROCEDURES: WEAR RESPIRATOR TO AVOID SMOKE INHALATION  
UNUSUAL FIRE AND EXPLOSION HAZARDS: NONE

### HEALTH HAZARD DATA

THRESHOLD LIMIT VALUE: NONE ESTABLISHED  
EFFECTS OF OVEREXPOSURE: NONE ESTABLISHED

EMERGENCY & FIRST AID PROCEDURES:

INGESTION CALL PHYSICIAN

**REACTIVITY DATA**

STABILITY:

STABLE

CONDITIONS TO AVOID:

N/A

HAZARDOUS DECOMPOSITION PRODUCTS:

CO<sub>2</sub>, CO, NITROGENOUS COMPOUNDS

HAZARDOUS POLYMERIZATION:

WILL NOT OCCUR

SPILL OR LEAK PROCEDURES:

N/A

STEPS TO BE TAKEN

N/A

MATERIAL TO BE SPILLED:

N/A

WASTE DISPOSAL METHOD:

APPROVED LANDFILL OR  
RECYCLING/REGRANULATION

For more information visit [www.expanko.com](http://www.expanko.com) or call 800-345-6202.