



Expanko Resilient Flooring
1000 East Park Avenue | Maple Shade, NJ 08052
800.345.6202 | sales@expanko.com | www.expanko.com



CHEMICAL RESISTANCE - ASTM F925

TECHNICAL SUPPORT 800.345.6202

- 5% Acetic Acid: No Change
- 70% Isopropyl Alcohol: No Change
- Mineral Oil: No Change
- 5% Sodium Hydroxide: No Change
- 5% Hydrochloric Acid: No Change
- 5% Ammonia: No Change
- Bleach: No Change
- 5% Phenol: No Change
- Gasoline: Slight Change
- Sulfuric Acid: No Change
- Kerosene: Slight Change
- Olive Oil: No Change

For more information visit www.expanko.com or call 800-345-6202.